



SAFE-T-GRIP® 1:1

PRODUCT DATA

PRODUCT DESCRIPTION

Safe-T-Grip® 1:1 is a two-component, 100% solids epoxy/amine cured polymer, that is designed for use with aggregate as a tough, durable, skid resistant, high friction bonded overlay. Safe-T-Grip® 1:1 is a liquid binder intended to be used in conjunction with either custom color aggregate manufactured by Epoplex or HFST approved aggregate. Safe-T-Grip® 1:1 is formulated to provide a simple volumetric mixing ratio of one part Component A to one part Component B.

USES, APPLICATIONS

Safe-T-Grip® 1:1 may be applied to concrete or asphalt surfaces as a long-lasting thin overlay to provide a skid resistant high friction surface in wet and dry weather conditions. Epoplex colored aggregate is available in a variety of colors, including bike path green and bus lane red. Possible uses for Safe-T-Grip® 1:1 include highway ramps, intersections, specialty lanes, school zones, cross walks, etc. Safe-T-Grip® 1:1 is not recommended for use over polymeric or magnesium phosphate patching materials.

PRODUCT ADVANTAGES

- 100% solids chemistry
- Epoxy chemistry maintains flexibility in cold and after aging
- Long-term high friction characteristics
- Excellent bond strength assures good adhesion to the substrate
- Special formulation chemistry for faster set at a wide range of temperatures
- Specified aggregate provides and maintains excellent skid resistance
- Low viscosity and 1:1 mix ratio for easy application

PACKAGING

Component A: Epoxy Resin

Component B: Amine

Both components are available in 5 gallon pails, 55 gallon drums and 250 gallon totes.

IMPORTANT:

Epoplex believes the information contained here to be true and accurate. Information contained here is for evaluation only. Epoplex makes no warranty, expressed or implied, based on this literature. We further reserve the right to modify and change products or literature at any time.

09/19
© 2019 Epoplex



PHYSICAL CHARACTERISTICS

Percent Solids100%
Viscosity1,250 cP (ASTM D-2196)
Gel Time @ 77°F/25°C15 minutes (ASTM D-2471)
Cure Time @ 77°F/25°C2.5 hours
Adhesion> 300 psi (100% concrete failure) (ASTM D-7234)
Hardness, Shore D70 (ASTM D-2240)
Tensile Strength2900 psi (ASTM D-638)
Elongation100% (ASTM D-638)
Water Absorption0.6% @ 24 hour (ASTM D-570)
Coverage:	
Liquid Binder0.36 gallons/sq. yd.
Aggregate15-18 lb/sq. yd.
Compressive Strength (Mortar)	
(ASTM C-579)After 3 hours - 1700 psi After 7 days - 5300 psi

Note: All properties are tested at 7 days unless otherwise noted.

STORAGE CONDITIONS

Store both components of Safe-T-Grip 1:1 in a dry area. Avoid excessive heat and do not freeze. The shelf life is two years in the original unopened container. Prior to use material should be conditioned to 65-85°F.

IMPORTANT:

Epoplex believes the information contained here to be true and accurate. Information contained here is for evaluation only. Epoplex makes no warranty, expressed or implied, based on this literature. We further reserve the right to modify and change products or literature at any time.

07/19
© 2019 Epoplex



1000 East Park Avenue, Maple Shade, NJ 08052 • 856.667.8399 • FAX 856.779.2963 • Toll Free 800.822.6920