

Safe-T-Grip® 1:1

General Application Specification

DESCRIPTION

This work shall consist of installing a textured friction surface in areas as designated on the plans and details in accordance with the plans and specifications.

MATERIALS

Use Safe-T-Grip® 1:1 as manufactured by Epoplex, 1000 East Park Avenue, Maple Shade, New Jersey 08052, a two part exothermic epoxy resin binder treatment, containing an epoxy/amine binder covered with natural or pigmented aggregate or an engineer-approved equal.

The binder shall consist of a thermosetting epoxy/amine compound which holds the aggregate firmly in position. The binder shall meet the following requirements:

PROPERTY	REQUIREMENT	TEST METHOD
Gel Time @ 77°F/25°C	10 minutes min.	(ASTM D-2471)
Cure Time @ 77°F/25°C	3 hours max.	
Adhesion	> 300 psi (100% concrete failure)	(ASTM D-7234)
Hardness, Shore D	65 min.	(ASTM D-2240)
Tensile Strength	2650 psi min.	(ASTM D-638)
Elongation	40% min.	(ASTM D-638)
Compressive Strength	@ 3 hours > 1,000 @ 7 days > 5,000 psi	
Water Absorption	1% max @ 24 hour	(ASTM D-570)
Coverage:		
Liquid Binder	0.36 gallons/sq yd for 60 mil application	
Aggregate	15-18 lb/sq yd	

Note: All properties are tested at 7 days unless otherwise noted.

The aggregate specified shall be as per the project specific requirements. The aggregate will be delivered to the construction site in clearly labeled 2000 pound super sacks, and it should be clean, dry, and free from foreign matter.

CONSTRUCTION REQUIREMENTS

The two-part modified epoxy binder material shall not be applied on a wet surface, or when the ambient and/or surface temperature is below 40°F or above 105°F, or when the anticipated weather conditions would prevent the proper application of the surface treatment as determined by the manufacturer.

Existing surfaces shall be cleaned by use of mechanical sweepers, high pressure air, or other methods approved by the Engineer prior to the installation. Receiving surfaces must be clean, dry and free of all dust, oil, debris and any other material that might interfere with the bond between the epoxy binder material and existing surfaces. Surfaces may need to be washed with a mild detergent and rinsed and dried using a hot compressed air lance. Remove any existing pavement markings as

deemed necessary by the manufacturer. Adequate cleaning of all surfaces will be determined by the engineer and/or manufacturer's representative. Cover and protect all existing pavement markings and utilities prior to placement. Clean and fill all inadequately sealed joints and cracks greater than 1/4" with a manufacturer's approved crack sealant.

A manufacturer's representative can be on site to provide technical assistance during the start up operations and as necessary during the surface preparation, material installation and during any necessary remedial work. Place the surface treatment in accordance with manufacturer's recommended methods at the thicknesses and details as shown in the contract documents.

APPLICATION OF THE TWO PART MODIFIED EPOXY BINDER COMPONENTS

The two-part modified epoxy binder utilized in the high-friction surface application can be hand applied, or applied using a self-contained plural component pumping system. The binder is mixed at a 1:1 ratio by volume.

If using a self-contained plural component pumping system, the system must be capable of continually mixing and delivering the components on demand via multiple spray guns. The unit needs to be capable of heating the components to the proper application temperature. Mechanically applied distributing equipment shall include accurate measuring devices and/or calibrated containers and thermometers for measuring the binder temperature and pressure prior to placement. The capacity of the system will be at a minimum of 500 gallons with a minimum spraying capability of 4 gallons per minute.

For application by hand, the material should be applied utilizing a notch squeegee to ensure uniform thickness and correct rate of coverage. The material should be squeegeed out and back rolled, using a medium nap roller. It is imperative to ensure that proper thickness is achieved. The goal thickness is 60 mils or as specified.

The two-part modified epoxy binder shall be uniformly distributed over the pavement section that is to be treated. The material shall be applied within the temperature range specified. Operations shall proceed in such a manner that will not allow the epoxy material to chill, set up, dry or otherwise impair retention of the covered aggregate.

The mixed components must be applied onto the cleaned surface at a minimum coverage rate of 0.36 gallons/square yard for 60 mil application. Immediately apply the aggregate onto the installed two-part modified epoxy binder, at a rate of approximately 15-18 lbs., or as specified, per square yard coverage (coverage of both the liquids and the aggregate is highly dependent on surface porosity. Contact the project engineer and/or the material manufacturer for specific project coverage).

Two-part epoxy materials not meeting the mixing ratio and specific gravity requirements will not be allowed. A notarized certificate of compliance shall be supplied upon request from the two-part modified epoxy resin manufacturer.


Utilities, drainage structures, curbs and any other structure within/adjacent to the treatment location shall be protected against the application of the surface treatment materials.

Allow the treatment to cure in accordance with manufacturer recommendations, approximately 2.5 hours at an ambient temperature of 75°F and rising. Remove the excess aggregate by mechanical means or suction sweeping truck before opening to traffic. Excess aggregate can be reused on the following day's installation. The aggregate must be clean, uncontaminated and dry.

IMPORTANT:

Epoplex believes the information contained here to be true and accurate. Information contained here is for evaluation only. Epoplex makes no warranty, expressed or implied, based on this literature. We further reserve the right to modify and change products or literature at any time.

09/19
© 2019 Epoplex



1000 East Park Avenue, Maple Shade, NJ 08052 • 856.667.8399 • FAX 856.779.2963 • Toll Free 800.822.6920