


EPOPLEX®



Safe-T-Grip 1:1 Viscosity vs. Temperature

1000 East Park Avenue • Maple Shade, NJ 08052 • 800.822.6920 • FAX: 856.779.2963

EPOPLEX® Safe-T-Grip 1:1 - Viscosity (cP)

Temperature	Hardener	Epoxy
80°F/27°C	480	3725
90°F/32°C	275	1835
100°F/38°C	170	1010
110°F/43°C	110	565
120°F/49°C	-	340

Note: Material temperatures below 120°F can be selected so that the viscosity of the components will coincide (within 10%), thus allowing for proper flow and mixing of the components.

© 2022 Epoplex

a brand of
STONHARD®