



EPOPLEX® LS90 - RETROREFLECTIVITY ON DELAWARE SR-1

Project location: SR 1 near Dover, Delaware
Owner: State of Delaware
Installation date: December 9, 2002
Surface preparation: 100% removal by grinding
Ambient temperature: 32° F.
Surface temperature: 27° F.
Cure time: 15-17 minutes
Material Used: Epoplex LS90 Polyurea
Glass beads used: Cataphote type IV virgin glass 80% round, M-247 recycled glass 75% round
Installer: Century Fence Company
Surface: Concrete
Data collected by: Delaware DOT
Date of last reading: 12/02 – 1/04
Number of readings: Unknown
Instrument used: LTL 2000

